

**TECHNICAL DATA**

**TYPICAL APPLICATIONS**

- > For use on Siat L33, L36, L233 (or equivalent) printing presses

**ADVANTAGES AND BENEFITS**


- > Directly Printable with all leading brands of solvent inks
- > Exclusive release coat technology allowing for consistent unwind, faster drying times resulting in more efficient use of machines
- > Superior ink anchorage without pickoff
- > Quiet off the roll

**CONSTRUCTION**

Overall Grade/Function: Production Grade  
Backing: 30 micron biaxially oriented, cast polypropylene film  
Adhesive: Synthetic rubber resin



**COLOR(S)**



**STANDARD WIDTH(S)**

144 mm    150 mm    288mm

**STANDARD LENGTH(S)**

914 m    1371 m    1828m

Contact your Shurtape sales representative for other available sizes.

**PHYSICAL PROPERTIES**

	STANDARD	METRIC
Thickness	1.9 mils	.05 mm
Tensile Strength (longitudinal direction)	27 lbs/in width	47.3 N/10 mm
Tensile Strength (transverse direction)	44 lbs/in width	75 N/10 mm
Elongation	130 %	130 %
Adhesion to Stainless Steel	44 oz/in width	4.82 N/10 mm
Holding Power to Fiberboard	10,000+ minutes	10,000+ minutes
Adhesion to Backing	4 oz/in width	.44 N/10 mm
Service Temperature Range	20 F to 150 F	-7 C to 66 C
Application Temperature Range	35 F to 110 F	2 C to 43 C

Physical and performance characteristics shown above are obtained from tests recommended by PSTC, ASTM, government agencies or Shurtape Technologies, LLC. Quality Assurance and Technical Service Departments and do not represent a guarantee of product performance. Individual rolls may vary slightly from these averages. The user should determine whether the product is fit for a particular purpose and is suitable for the user's method of application before use.

**APPLICABLE SPECIFICATIONS**

ASTM D-1974; A-A-1684C

**STORAGE & USAGE CONDITIONS**

Tape should be stored in its original packaging in a cool, dry area away from direct sunlight and should be used within 12 months of date of shipment. Surfaces to which tape is applied should be clean, dry and free of grease, oil or other contaminants.

"Shurtape" is a registered trademark of Shurtape Technologies, LLC

Form# TDSHP 260 04/28/2009